300D Polyester Oxford 15K/5K White Membrane

Fabric reference: PX22 / RTGEN4

Specification	Published value
Base fabric	Polyester DTY 300D plain Oxford
Construction	Woven Oxford with membrane lamination
Finish / coating	C6 strong water and oil repellency + breathable white PU membrane lamination
Hydrostatic pressure	15,000 mm
Breathability	5,000 g/m²/day
Wash durability	60°C, 20 washes: grade 3
Typical project direction	High-performance rainwear and severe-weather outer shells

Source and scope

Source: Brilliant-Tex processing sheet as published in the TEC catalog. This sheet records the published values for product review. Confirm the applicable test methods and final bulk specification in writing.

Contact: info@brilliant-tex.com | WhatsApp +86 159 0095 5010